

DARASET® 400

Set-accelerating admixture

ASTM C494 Type C

Product Description

Daraset® 400 is a non-corrosive, non-chloride admixture for concrete. It accelerates cement hydration resulting in shortened setting times and increased early compressive and flexural strengths. Daraset 400 does not contain calcium chloride and is formulated to comply with ASTM C494 Type C, and can be used at any dosage to comply with ACI 318 guidelines for chloride content of concrete. Daraset 400 weighs approximately 11.9 lbs/gal (1.43 kg/L).

Uses

Daraset 400 set accelerator may be used wherever it is desirable to reduce the setting time of concrete and/or to increase its early compressive and flexural strengths. For mixes designed with pozzolans, such as fly ash or slag, Daraset 400 set accelerator can help offset the retarding effects of these materials, especially in cooler temperatures.

In cold weather, Daraset 400 may be used to reduce the time that it takes the concrete to set, prior to finishing. Typical results show that when concrete containing Daraset 400 is poured at 50°F (10°C), the concrete will set up to 2 hours faster than the reference concrete.

When used in the manufacture of precast concrete, Daraset 400 speeds the concrete's

strength development allowing for earlier form removals and more efficient production. Daraset 400 can also be used in masonry mortar to obtain higher early strengths and accelerated setting time effects.

Special Feature

Daraset 400 set accelerator provides setting time results and early strength development similar to that provided by calcium chloride, but without the potential corrosive effects. Daraset 400 can, therefore, at recommended dosage rates, safely be used where the potential corrosion of embedded or stressed steel must be avoided. It can also be used in concrete that is to be placed on steel clad or zinc coated steel decks where corrosion must be similarly avoided.

Performance

In concrete mixtures, Daraset 400 accelerates the chemical reaction between Portland cement and water. It speeds up the formation of gel—the binder that bonds concrete aggregates together. Accelerated gel formation in turn shortens the setting time of concrete, compensates for the set-slowing effects of cooler weather, and contributes to the development of higher early strengths.

Product Advantages

- Accelerates setting time
- Increases early compressive and flexural strengths
- Offsets the retarding effects of pozzolans such as slag or fly ash
- Non-corrosive
- Complies with ASTM C494 Type C



Addition Rates

The amount of Daraset 400 used will depend on specific job conditions, on local materials and on the degree of set acceleration and early strength development required. Typical addition levels range from 10 to 60 fl oz/100 lbs (650 to 3910 mL/100 kg) of cement. Higher dosage rates may be used for select applications after consulting with your local Grace sales representative.

Compatibility with Other Admixtures and Batch Sequencing

Daraset 400 is compatible with most Grace admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that Daraset 400 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see Grace Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations. Daraset 400 should not come into contact with any other admixture before or during the batching process, even if diluted in mix water.

Pretesting of the concrete mix should be performed before use, and as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as Daravair® or Darex® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your Grace representative for guidance.

Packaging & Handling

Daraset 400 is currently available in bulk quantities by Grace metered systems, or in 55 gal (210 L) drums. Daraset 400 freezes at approximately -10°F (-23°C), but its set acceleration, strength gain and non-corrosive properties are completely restored by thawing and thorough agitation.

Dispensing Equipment

A complete line of accurate dispensers is available. While Daraset 400 may be added to the mix on the sand or in the water, for greatest effectiveness, we recommend Daraset 400 be added at the end of the batch cycle.

Similar to all concrete admixtures, Daraset 400 should not come into contact with other admixtures prior to entering the concrete.

Specifications

The set-accelerating admixture shall be Daraset 400, non-chloride set accelerator, as manufactured by Grace Construction Products. The admixture shall be used in strict accordance with the manufacturers' recommendations. The admixture shall comply with ASTM Designation: C494 Type C and will not contain purposely added chlorides or contribute to steel corrosion. DARASET 400 is NSF Std. 61 certified when used at a maximum addition rate of 40 fl oz/100 lbs (390 mL/100 kg) of cementitious material. Certification of compliance will be made available upon request.

Concrete shall be proportioned in accordance with *Recommended Practice for Selecting Proportions for Normal Weight Concrete*, ACI 211.1 or *Recommended Practice for Selecting Proportions for Structural Lightweight Concrete*, ACI 211.2, or in accordance with ACI 318.

www.grace.com/construction

North American Customer Service: 1-877-4AD-MIX1 (1-877-423-6491)

Daraset, Daravair and Darex are registered trademarks of W. R. Grace & Co.—Conn.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the users' consideration, investigation and verification, but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would infringe any patent or copyright. W. R. Grace & Co.—Conn., 62 Whittemore Avenue, Cambridge, MA 02140. In Canada, Grace Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This product may be covered by patents or patents pending.
DS-31G 07/14

Copyright 2014. W. R. Grace & Co.—Conn.
GCS/PDF

GRACE